




Canfor Pulp Limited Partnership operates the Prince George, Intercontinental, and Northwood Pulp Mills in Prince George. The Intercontinental and Northwood Pulp Mills each produce ECF 90 which is a mixture of softwood species indigenous to the north central interior of British Columbia. The highly versatile fibre properties of our ECF 90 make it suitable for use in the manufacturing of a wide variety of products, especially those requiring the highest tensile strength.

Inherent Pulp Properties

Brightness (%ISO)	89 (delivered)
Dirt Levels mm ² /kg/ppm	Typically less than 2 mm ² /kg or 1 ppm
0.5% CED Viscosity (mPa.s)	21.0

Typical Species Analysis

Lodgepole Pine	70
White Spruce	25
Sup-alpine Fir	5





Fibre Properties (Kajaani FS 200)	
Weight Weighted Length (mm)	2.8
Coarseness (mg/m)	0.191

Bale Characteristics	Northwood	Intercon
Length (cm)	83	85
Width (cm)	83	79
Height (cm)	41	40
Weight (kg)	247.5	250

Typical Response To Refining On A 12 Inch Sprout Bauer Disc Refiner

Specific Energy (kW*hr/tonne)	Freeness CSF (mls)	°SR (°)	Breaking Length (km)	Tear Index mN.m ² /g	Burst Index (kPa.m ² /g)	Density (g/cm ³)
0	689	17.0	3.6	25.7	2.2	0.54
49	600	21.0	6.5	20.2	4.5	0.58
102	500	25.0	8.3	17.0	6.1	0.62
208	300	40.0	10.2	13.0	7.7	0.66



Interpolations	@ 4 km	@ 5 km	@ 7 km	@ 9 km	@ 10 km
Tear Index (mN.m ² /g)	27	24.5	19.3	15	12.9

Typical Response to Refining on a PFI Mill

Freeness CSF (mls)	°SR (°)	Breaking Length (km)	Tear Index MN.m ² / g	Burst Index (kPa.m ² / g)	Bulk (cm ³ / g)
701	17.5	4.6	26.3	3.2	1.66
600	21.0	10.1	11.7	8.1	1.43
500	25.0	11.2	10.1	9.0	1.39
300	40.0	12.0	9.4	9.6	1.34

The pulp and fibre properties listed here are based on long-term averages. Results on individual samples may vary from the values listed above. Pulp Evaluations are done using a 12-inch Sprout Bauer Refiner. Handsheets are prepared and tested based on PAPTAC/TAPPI/ISO procedures and are conditioned at 50% Relative Humidity at 23°C.